

VISCOM-DIGITAL - SOFT VINYL

Issue date : 22/09/2011
Date last modification : 22/09/2011**06475 - RI-JET 145 PERM/GREYOUT****WK 135 RIT/GRY****Face Material**

Gloss white soft vinyl.

Type	Soft vinyl		
Colour and Finish	Gloss white		
Weight	110 g/m ² ±10%	ISO-536	
Thickness	80 µ ±10%	ISO 534-80	

Adhesive

Acrylic permanent adhesive with grey pigmentation and very high cohesion. Designed for a wide variety of substrates such as glass, ABS, PS, PVC. Unsuitable for apolar surfaces (like PE and PP).

Reference	AP900 Grey		
Type	Acrylic permanent		
Min. Appl. Temp.	+10°C		
Service Temp.	-30°C/+120°C		
Shear	Very High		
Tack	6 N/25mm	FINAT FTM9	
Final Adhesion	9 N/25mm	FINAT FTM2	

This adhesive complies with FDA 175.105.

Liner

Type	One side siliconised clay coated Kraft		
Colour and Finish	White		
Weight	135 g/m ² ±10%	ISO 536	
Thickness	145 µ ±10%	ISO 534	
Transparency	n.a. %	DIN 53 147-64	

Applications

For promotional graphics and point of sale advertising with medium outdoor durability where is requested an higher opacity of the film

Printing Methods

Solvent and eco-solvent ink-jet printing. The RI-JET series of ink jet print media give excellent print results with UV ink-jet printing. Testing for suitability between media, printers and inks is always recommended prior to use. Testing for suitability between media, printers and inks is always recommended prior to use.

Shelf life

36 months, applicable only to the material delivered by Ritrama which has **not** undergone further processing, under the following **STORAGE CONDITIONS**:

- This material must be stored at a temperature of 22°C ± 2°C and 50 ± 5% of Relative Humidity.
- Storage area must be dry and clean.
- Keep the material in the original packaging when not used in order to protect it from dust and contamination.
- Do not expose to direct sunlight or heat sources.

All Ritrama products are subject to strict manufacturing controls to guarantee good quality products. The above information is based on research believed to be reliable, but does not constitute a warranty. All material should be tested by the purchaser to determine suitability of the product for their purposes. All information is subject to change without prior notice.

